

NABERAN

CORDES
ROPES
CUERDAS

CORDES TRESSÉES
BRAIDED ROPES
CUERDAS TRENZADAS

CORDES TRESSÉES · **BRAIDED ROPES** · CUERDAS TRENZADAS



NYLON

Ø mm	POIDS WEIGHT PESO 100 mts	CHARGE RUPTURE BREAKING STRENGTH CARGA ROTURA
6	2.25	750
8	4.00	1.350
10	6.20	2.080
12	8.90	3.000
14	12.20	4.100
16	15.80	5.300
18	20.00	6.700
20	24.50	8.300
22	30.00	10.000
24	35.50	12.000
26	42.00	14.000
28	48.50	15.800
30	55.50	17.800
32	63.00	20.000

POLIESTER

Ø mm	POIDS WEIGHT PESO 100 mts	CHARGE RUPTURE BREAKING STRENGTH CARGA ROTURA
6	12.70	565
8	4.80	1.020
10	7.60	1.590
12	11.00	2.275
14	14.80	3.180
16	19.50	4.060
18	24.50	5.080
20	30.50	6.355
22	36.70	7.620
24	43.70	9.140
26	51.20	10.710
28	59.40	12.240
30	68.20	13.670
32	77.80	15.700

NABERAN SAREAK S.L.

Mutrikuko Industrialdea 15
20830 Mutriku - Gipuzkoa
+34 943 195 122 | naberan@naberan.com

NABERAN FRANCE SARL

Avenue de la République
ZA Poriguenor | 29730 Le Guilvinec (France)
+33 298 582 739 | david@naberan.com